

EXTRABLOCK 330

SHADE FABRIC


EYE CATCHING
COLOURS AND FIRE
RATED OUTDOOR
SHADE



FABRIC SPECIFICATIONS

EXTRABLOCK 330

Shade Factor % (SF depends on colour - see below for details)	81 - 97
UVR Block %	96 - 98
UPF (UV Protection Factor)	21 - 41
Roll Width	3.0m
FRAS1530.2	Flammability 1, Spread Factor 0, Heat Factor 1
FR AS1530.3	Ignitability 13, Spread of Flame 7, Heat Evolved 2, Smoke 5
CSFM	Complies with California State Marshals requirements, Title 19, Section 1237




PEARL ONYX

FR




CREAM

SF=81%




BEIGE

SF=87%



LATTE


SF=80%



MINT GREEN


SF=93%

FR



PERSIAN GREEN

FR



FOREST GREEN


SF=93%

FR



OLIVE GREEN

FR




CHOCOLATE

FR



DOVE BLUE

FR



LIME GREEN

SF=86%

FR



TRUE BLUE

SF=95%

FR



NAVY

SF=95%

FR



SILVER

SF=98%

FR



CHARCOAL

SF=92%

FR



MIDNIGHT

SF=97%

FR



YELLOW

SF=75%



RED

SF=88%



SUNBLAZE

SF=95%


FR



OXIDE RED

SF=88%

FR



PURPLE

SF=88%

FR



Cream, Beige, Yellow and Red are not FR. Colours shown indicative only.

FEATURES



The EXTRABLOCK range of knitted shade fabric has been specifically designed for use in tension structures and shade sails, but performs equally well when used on carpark structures, awnings and umbrellas.

EXTRABLOCK is one of the worlds best FR rated shade cloths. It meets the California State Fire Marshall test for title 19. This is widely recognised as the most difficult FR test to meet and EXTRABLOCK gets a new certificate every year!

EXTRABLOCK is a very dimensionally stable shade cloth with very similar biaxial strengths and extensions in both directions.

EXTRABLOCK has a 12 year warranty against UV breakdown. Peace of mind for you and your clients.

- ✓ High Strength fabric
- ✓ Controlled Elongation
- ✓ Maximum protection with up to 98% shade
- ✓ Excellent Dimensional Stability
- ✓ 12 Year Warranty
- ✓ Fire retardancy rated
- ✓ Heat set (stentered)
- ✓ Will not rot or support the development of mould and mildew
- ✓ Breathable, allowing air circulation for cooling



ENGINEERING SPECIFICATIONS



Breaking Force Warp (AS2001.2.3.2-2001 Grab Method)	979N
Breaking Force Weft (AS2002.3.1-2001)	1228N
Elongation at Break Warp	67%
Elongation at Break Weft	57%
Bursting Strength (AS 2001.2.4-1990)	3000kPa
Tear Resistance Warp (AS2001.2.10-1986)	157N
Tear Resistance Weft (AS2001.2.10-1986)	170N

EXTRABLOCK 330

EXTRABLOCK 330 Shade Mesh is part of a range of high-end fabrics distributed by Shadetex Sails

www.shadetex.com



SHADETEX SAILS
SUPERIOR SUN SHADE

EXTRABLOCK 330

PURPLE

AVAILABLE FROM: